



Specification Sheet – HydraCX™ Extreme Slope Matrix

DESCRIPTION

The HydraCX Extreme Slope Matrix shall be a hydraulically-applied mulch composed of a patent-pending blend of mechanically processed straw fibers, reclaimed cotton plant materials, performance-enhancing tackifiers, and other proprietary additives. The HydraCX matrix requires no curing for soil erosion protection and establishes an intimate bond upon application with the soil's surface to create a continuous, porous, absorbent, and flexible erosion control matrix that allows for rapid germination and accelerated plant growth.

The all natural fiber mulch shall satisfy the control performance criteria set forth in the Ceriodaphnia dubia, Daphnia magna and Pimephales promelas tests as described in EPA documentation (USEPA 2002) and the Region VIII Whole Effluent Toxics Control Program (EPA Region VIII 1997); therefore illustrating no significant toxicity for the mulch.

Composition: All components of the HydraCX matrix shall be pre-packaged by the Manufacturer to assure material performance and in compliance with the following values. Under no circumstances will field mixing of additives or components be accepted.

Material Content	
Mechanically Processed Straw	65% +/- 3%
Mechanically Processed Reclaimed Cotton Plant Material	25% +/- 3%
Proprietary Hydro-colloidal Tackifiers and Activators	10% +/- 1%

Specifications	
Contents	Straw/Reclaimed Cotton Plant Material
Packaging	50 lbs (23 kg) +/- 3%
Total Organic Matter	90.0% +/- 4%
Carbon to Nitrogen Ratio	< 38:1*
Moisture Content	12% +/- 3%
Color	Natural Green

*Analysis concluded from a representative sample as the C:N ratio may vary from sample to sample



800-452-4435
 info@jenhill.com
 www.jenhill.com

Index Property	Test Method	Typical
Thickness	ASTM D6566	0.18 in. (4.6 mm)
Mass/Unit Area	ASTM D6525	13.45 oz/sy (457 g/sm)
Ground Cover	ASTM D6567	97.9%
Organic Matter	ASTM D2974	93.64%
Water Holding Capacity	ASTM D7367	880%
Acute Toxicity	EPA 2021.0-1	Non-Toxic
Functional Longevity	Observed	Up to 12 months
Cure Time	Observed	No cure time
Color	Observed	Green

Performance Property	Test Method	Typical
Rainfall Event (R-factor)	ASTM D6459*	231 < R
Cover Factor	ASTM D6459*	0.001
Percent Effectiveness	ASTM D6459*	99.9%
Vegetation Establishment	ASTM D7322	>550%

* Modified ASTM D6459 (Standard Test Method for Determination of Erosion Control Blankets (ECB) Performance in Protecting Hillslopes from Rainfall-Induced Erosion)

Packaging
Bags are filled with 50 lbs (23 kg) of material and packaged in a UV and weather-resistant bag. Each pallet contains 40 bags or one ton of material with a plastic cover for enhanced protection from rain and UV rays.

NOTE: Not for use in channels, swales, or other areas where concentrated flows are anticipated, unless installed in conjunction with a temporary erosion control blanket or permanent turf reinforcement mat. HydraCX may be applied on saturated surfaces. Do not allow foot traffic or grazing on treated areas until vegetated. Be cautious of slippery surfaces while applying. Warning: Do not store near an open flame or heat source. Use caution when stacking units. See Installation guide for more detailed information regarding application of the HydraCX product.



Tensar International Corporation
 2500 Northwinds Parkway
 Suite 500
 Alpharetta, GA 30009
 800-TENSAR-1
 tensarcorp.com

Tensar International Corporation warrants that at the time of delivery the product furnished hereunder shall conform to the specification stated herein. Any other warranty including merchantability and fitness for a particular purpose, are hereby executed. If the product does not meet specifications on this page and Tensar is notified prior to installation, Tensar will replace the product at no cost to the customer. **This product specification supersedes all prior specifications for the product described above and is not applicable to any products shipped prior to January 1, 2012.**

©2013, Tensar International Corporation

EC_HMX_MPDS_HYDRACX_6.13